


APPENDIX B

EXAMPLE: FIELD PROCEDURE FOR CLARENCE CANNON DAM

Example: Condition 1 Field Procedure for Clarence Cannon Dam


PRESSURE TEST RESULTS

WATER TAKE (CF14)	WATER/RATIO W/C
UP TO 4	6:1
4 - 6	5:1
6 - 7	4:1
7+	3:1



(NOTE: NUMBERS ARE EXAMPLES ONLY. DO NOT APPLY TO EVERY JOB.)

Example: Condition 2 Field Procedure for Clarence Cannon Dam



Example: Condition 3 Field Procedure for Clarence Cannon Dam

Once the rate of grout take has begun to steadily decrease, the mixture shall not be thickened further.

If there is a rapid decrease in the rate of grout take, the mixture should be thinned.